

# Antox® 2001T

Pickling and Polishing Paste for Stainless Steels

A Product of the Chemetall Group

## Field of Application

The removal of high temperature oxide scale and annealing colors in the areas of weld seams (only WIG seams) and heat-influenced zones.

The cleaning of stainless steel equipment with heavy contamination or rust.

## Working Tools

- Wooden spatula for applying the paste.
- Cleaning felt for polishing.

## Application and Procedure

Before commencing work, safety precautions must be observed and protective equipment made use of.

*Antox 2001 T* is to be stirred with a plastic or wood stirrer before use, or shaken well.

*Antox 2001 T* is to be painted generously on the places to be treated. The reaction time should be observed.

Use the felt to rub in with circular or longitudinal movements until no more oxide layer or contamination (particles of rust) can be seen.

Upon completion, the processed surface is to be rinsed under cold water, using a high pressure water jet appliance (at a pressure of at least 120 bar).

## Reaction Time Periods

Rust and acid-resistant steels, stainless steels	10 - 15 minutes
Edelstahl, glänzend	1 - 3 minutes

The reaction time period is dependent on the quality of the working materials treated as well as on the temperature of the ambient air and materials. The optimal treatment temperature is around 18 - 22° C. Work routines should be avoided in direct sunlight (due to hazard of premature drying).

## Yield

1 kg of Antox 2001 T is sufficient for approx. 80 -100 running meters of weld seam with heated area.

## General Remarks

*Antox 2001 T* contains no hydrochloric acid and no chloride.



**Chemetall (Schweiz) AG, Silostrasse 7, CH-5606 Dintikon**

Phone: +41(0)56 616 90 30 Fax: +41(0)56 616 90 40

E-Mail: chemetall.schweiz@chemetall.com

„A company of mg chemical group Dynamit Nobel“

## Notes on hazards and suggestions for safety precautions

*Antox 2001 T* contains hydrofluoric acid and nitric (azotic) acid.

Toxic if breathed in, swallowed or in contact with the skin.

Process and store in a well-ventilated place (the cans should be tightly closed). Breathing apparatus should be used when ventilation facilities are insufficient. Appropriate protective goggles, gloves and clothing should be worn whilst working.

Contact with the eyes should be treated by thorough rinsing with water and thereafter a doctor should be consulted. Contaminated and soaked protective clothing should be immediately changed. A doctor should be consulted if nausea is experienced (the doctor should be shown the notes on safety precautions, the product notes or the product label).


Please also observe the detailed information given in the German DIN Standard "SIDA" safety data sheet.

These products should not be accessible to children. For commercial and industrial use only.

## Disposal

Neither *Antox 2001 T* nor the rinsing water may be disposed of in the public sewers in an untreated state. The waste water is acidic and contains alloy residue solids from the treated metal. Appropriate treatment should be carried out in a suitable neutralisation plant or disposal undertaken via a licensed waste disposal enterprise. The local waste water regulations are to be observed.

**This edition replaces all previous editions, which then lose their validity. The information and details are given to the best of our knowledge and belief, and conform, at the time of going to print, to the forementioned experience in laboratory situations and in practice. These are however only to be understood as non-binding guidelines, which will have to be adjusted individually to meet the requirements of every situation in practice. As the application and use of our products are outside our control and influence, we can only accept liability for the irreproachable, standard quality of the products at the moment in time of delivery. Any consequential loss or damage will only be addressed when the possibility of such has been previously agreed in writing before application and use, by making reference to the advertised and warranted characteristics and effects.**



**Chemetall (Schweiz) AG, Silostrasse 7, CH-5606 Dintikon**

Phone: +41(0)56 616 90 30 Fax: +41(0)56 616 90 40

E-Mail: chemetall.schweiz@chemetall.com

„A company of mg chemical group Dynamit Nobel“